

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C07C 29/149		A1	(11) International Publication Number: WO 99/35114
			(43) International Publication Date: 15 July 1999 (15.07.99)
(21) International Application Number: PCT/EP99/00016 (22) International Filing Date: 5 January 1999 (05.01.99) (30) Priority Data: 9800011 8 January 1998 (08.01.98) BE (71) Applicant (for all designated States except US): EURODIOL S.A. [BE/BE]; Parc Industriel Zone A, B-7181 Feluy (BE). (72) Inventor; and (75) Inventor/Applicant (for US only): BERTOLA, Aldo [IT/IT]; Via Luigi Illica, 5, I-20121 Milano (IT). (74) Agent: SARPI, Maurizio; Studio Ferrario, Via Collina, 36, I-00187 Roma (IT).			(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: PROCESS FOR THE PRODUCTION OF BUTANEDIOL BY LIQUID PHASE HYDROGENATION			
(57) Abstract Process for the production of 1,4-butanediol by mixed phase catalytic hydrogenation of gamma-butyrolactone, succinic anhydride esters, or mixtures thereof.			

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakhstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

Process for the production of butanediol by liquid phase hydrogenation.

Description.

The present invention relates to a process for the production of 1,4-butanediol, and particularly it relates to the employment of mixed phase flow catalytic hydrogenation of gamma-butyrolactone, succinic anhydride esters, or mixtures thereof .

It is known from the prior art that there exist several processes for production of 1,4 butanediol (BDO) from dicarboxylic acid esters with four carbon atoms as starting materials.

10 In USSR Patent N°400,567 a copper chromite catalysed liquid phase conversion of esters into BDO at temperatures ranging between 280 and 300 °C and 300 bar pressure is given.

15 In US Patent N°4,613,707 a conversion of diethylsuccinate into BDO at 200 °C T and 135 bar pressure with a mainly copper and aluminium borate catalyst is given.

20 In US Patent N°2,079,414 a vapour phase hydrogenation of esters is given, on a copper chromite type catalyst and temperatures ranging between 300 and 400 °C

In US Patent N°204,944 a broad description of both liquid and vapour phase ester hydrogenations is given, using copper chromite catalysts. In one example, 25 a liquid phase butyl succinate hydrogenation at 207 bars is described.

In US Patents N°'s 4,584,419 and 4,751,334,

owned by Davy Mc Kee Ltd. (U.K.) processes for the large scale production of BDO are described, wherein 4 carbon dicarboxylic acid hydrogenations are resorted to.

5 In the above processes, the hydrogenation reactions take place in two sequential stages in the vapour phase, and in the presence of a copper chromite type hydrogenation catalyst.

 According to the processes assigned to Davy
10 Mc Kee Ltd., each of the two hydrogenation stages occurs in the conditions ranging between the following values:

 Pressure: between 25 and 70
 bars

15 Temperature: between 150° and 200
 °C

 H₂/ester ratio: between 100/1
 and 800/1

 1,4-butanediol synthesis from gammabutyrolactone (GBL)
20 is mentioned in German Patent N°2,144,316, assigned to Mitsubishi Corporation of Japan. Conversion is carried out on a nickel-cobalt catalyst, at temperatures between 200 and 250 °C and pressures between 100 and 120 bars.

25 In Belgian Patent N°892,958 a vapour phase hydrogenation process of GBL to BDO is given, at pressures between 15 and 30 bars, and temperatures ranging between 200 and 230 °C, on a copper-zinc oxide based catalyst.

30 In US Patent N°4,652,685 a similar process is

described, and this is carried out in the vapour phase and at 40 bar pressure, 210 °C and on a barium stabilised copper chromite type catalyst.

In German Patent N°3,903,563 a process is
5 described wherein reaction pressure is 60 bars and a cobalt-copper catalyst is employed.

The conditions to maintain vapour or mixed flow conditions being strictly necessary, all solutions so far proposed for a process for the production of
10 1,4-butanediol present two types of problems both of which considerably affect costs.

One relates to the large amount of hydrogen needed, more so if compared with the actual amount of this gas which goes to react with the starting
15 material; the other stems from the need to reduce the catalyst before use, operation which is also time consuming, as it entices an at times long phase prior to the process itself.

It is therefore an aim of the present
20 invention to propose a process for the production of 1,4-butanediol which is speedy and cost effective as in this catalysts in their unreduced forms are used, and a very much smaller amount of H₂ is used than in anyone of the processes objects of the patents and
25 methodologies in the prior art.

Such aims are accomplished by a process for the production of butanediol by selective catalytic hydrogenation of gamma-butyrolactone, succinic anhydride esters or mixtures of gamma butyrolactone and
30 succinic anhydride esters, characterised by the fact

that it occurs in at least two catalytic stages at a pressure ranging between 60 and 100 bars and temperature ranging between 160 and 250 °C which are characterised with the presence of a liquid phase at
5 the entrance of the first stage.

These and other features will be more readily apparent from the following description of a preferred not limiting embodiment of the invention with reference to the accompanying drawing in which a scheme of the
10 production process is shown.

In the process object of the present invention, BDO production takes place starting from GBL, succinic acid esters or mixtures thereof which are mixed phase flow hydrogenated in the presence of
15 suitable hydrogenation catalysts, and at reaction pressure and temperature, using those catalysts that allow high yields and selectivity.

The process object of the present invention results to be more advantageous, with respect to all
20 those processes for the production of butanediol where the hydrogenation is carried out in the vapour phase, as in this smaller hydrogen volumes are required and nevertheless a higher selectivity and conversion can be achieved.

25 Furthermore, the large scale reactions are carried out at temperatures and pressures that allow remarkable savings when compared with the processes described in the literature mentioned above.

Moreover, this process results to be
30 particularly advantageous if it is associated with a

GBL production process which starts from maleic or succinic anhydride esters. In fact, in the GBL production process, together with GBL, an azeotropic mixture consisting of GBL and an unconverted succinic acid ester, dimethylsuccinate (DMS) for instance, is produced. Such a mixture is a nearly ideal starting material in the process which is object of the present invention.

The process object of the present invention is valid even just using a succinic acid ester, namely DMS for example, as starting material. This can be obtained by hydrogenation of the corresponding maleic anhydride ester.

The catalysts employed are of the copper-zinc oxide type, all in the non-reduced form, consisting of 20-35 % copper, and 25-40% zinc, with a surface area which is not any lower than 30 m²g⁻¹.

Likewise, copper chromite catalysts can be employed, these containing from 40 to 50% copper oxide, from 40 to 50% chromium oxide, from 5 to 15% barium or manganese oxide, with a surface area which is not any lower than 20 m²g⁻¹.

To achieve temperature control in the reaction, it is better to let the reaction occur in at least two stages, allowing for cooling down the fluid between the two stages with a cold hydrogen supply.

The molar ratio between hydrogen and shot at the entrance of the first stage is between 10 and 100, preferably between 20 and 60, while at the entrance of stage two it is between 30 and 150, preferably between

50 and 100.

The overall space velocity measured on a liquid base, is between 0.1 and 1.0 hr⁻¹, preferably between 0.2 and 0.4 hr⁻¹.

5 The operating pressure in the process ranges between 60 and 100 bars, preferably between 75 and 90 bars.

 The operating temperature of the reaction in the process ranges between 160 and 250 °C, preferably
10 between 200° and 220 °C.

 A scheme of the process is shown in the enclosed drawing. The operating parameters given refer to a starting material consisting of a GBL and DMS mixture, in the 70:30 ratio. The loading mixture (line
15 1) and a recycled liquid stream containing GBL from fractionation unit 20 (line 2), is mixed with a preheated hydrogen stream (line 3), and fed to a liquid vapour distributor which is placed higher than first reaction stage 4. At the end of the first reaction
20 stage 4 the outgoing liquid-vapour mixture is cooled by cold hydrogen injection (line 5), and goes to feed the following reaction stage 6, after flowing through another liquid-vapour distributor. The overall reaction conditions and performances are the following:

25	Pressure:	80 bar
	Temperature:	180-220°C
	Molar Ratio H ₂ : shot (I stage):	30
	Molar Ratio H ₂ : shot (2 stage)	80
	Catalyst:	copper-
30		zinc oxide

	Liquid Hourly Space Velocity(LHSV):	0.35 hr ⁻¹
	DMS Conversion	98%
	GBL Conversion	90%
	Selectivity:	
5	Butanediol	90.5 %mol
	Tetrahydrofuran	9.0 %mol
	Butanol and other byproducts	0.5 %mol

The effluent from the reactor (Line 7) cools down in the exchanger 8, giving heat to the recycled hydrogen rich stream, and in exchanger 9 after that, and ends up feeding separator 1 (Line 10) where a liquid organic phase separates from a hydrogen rich gaseous phase. The gaseous phase from separator 1 (Line 13) is compressed by compressor 14, and is then recycled to the reaction cycle. A fraction of the recycled gas is purged (Line 15) to avoid excessive deposition of inert material.

Compressed gas (Line 16) together with the hydrogen feedstock (Line 17) partly (line 5) mixes with the effluents from reaction stage 1 and partly (line 18) preheats in exchanger 8 and heater 19, to feed reaction stage 1 (4), together with the shot (line 1) and the recycled material (line 2).

The liquid organic phase from separator 11 feeds (line 12) fractionation unit 20, where an unconverted GBL rich recycle stream (line 2), THF (line 21), methanol (line 22), water and light organic byproducts (line 23), heavy organic by-products (line 24), and BDO (line 25) separate. The process allows production of BDO and partly of THF in a simple and

cost effective way, and with great operational flexibility. The process makes BDO, and partly THF production possible.

The cost effectiveness of the present process
5 is especially emphasised in case the BDO production unit described with the process object of the present invention, is integrated with a GBL and THF production unit wherein starting materials are maleic anhydride esters.

10

Claims.

1. Process for the production of butanediol by selective catalytic hydrogenation of gamma-butyrolactone, succinic anhydride esters or mixtures of gamma butyrolactone and succinic anhydride esters, characterised by the fact that it occurs in at least two successive catalytic steps which are characterised at a pressure ranging between 60 and 100 bars and temperature ranging between 160 and 250 °C, and by the presence of a liquid phase at the entrance of the first stage.

2. A process according to claim 1 wherein the reaction is carried out operating at a pressure ranging between 75 and 90 bars, and temperature ranging between 200 and 220 °C.

3. A process according to claim 1, wherein the molar ratio between hydrogen and shot at the first stage ranges between 10 and 100, and the molar ratio between hydrogen and shot in the following one or more stages ranges between 30 and 150.

4. A process according to claim 3, wherein the reaction is carried out at a molar ratio between hydrogen and shot which ranges between 20 and 60 at the entrance of the first stage, and between 50 and 100 at the entrance of the following one or more stages.

5. A process according to claim 1, wherein reaction temperature of the reaction is controlled cooling down the fluid between the reaction stages by supplying cold hydrogen.

6. A process according to claims 1 ,

wherein the succinic anhydride ester alkyl group consists of between 1 and 4 carbon atoms.

7. A process according to claims 1,2,3,4 and 5 wherein the catalyst employed is copper and zinc oxide based, and consists of between 20 and 35% copper, and between 20 and 40 % zinc,

8. A process according to claim 7, wherein the catalyst has both its components in their unreduced forms.

10 9. A process according to claims 7 and 8, wherein the catalyst has a surface area which is not any smaller than $30 \text{ m}^2\text{g}^{-1}$

10. A process according to claims 1,3,4 and 5 wherein a stabilised copper chromite catalyst is employed, which consists of between 40 and 50% copper oxide, of between 40 and 50 % chromium oxide, of between 5 and 15% barium or manganese oxide.

11. A process according to claim 10, wherein the catalyst has all its components in their unreduced forms.

12. A process according to claim 10 and 11, wherein the catalyst has a surface area which is not any smaller than $20 \text{ m}^2\text{g}^{-1}$.

13. A process according to claims 1,3 and 7 or 9 wherein the hydrogen and shot ester mixture in the shot contact the catalyst at an overall liquid hourly space velocity ranging between 0.1 and 1.0 hr^{-1} .

14. A process according to claim 13 wherein the reaction is carried out at an overall liquid hourly space velocity that ranges between 0.2 and 0.4 hr^{-1} .




FIG. 1

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 99/00016

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 C07C29/149

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C07C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 4 751 334 A (K. TURNER, ET AL.) 14 June 1988 cited in the application see column 3 - column 4 ---	1
A	BE 892 958 A (DAVY MCKEE (OIL & CHEMICALS)) 16 August 1982 cited in the application see page 6 ---	1,7
A	US 4 652 685 A (J.N. CAWSE, ET AL.) 24 March 1987 cited in the application see column 2 - column 3; examples -----	1,10

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

10 June 1999

Date of mailing of the international search report

21/06/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

English, R

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 99/00016

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 4751334 A	14-06-1988	BR 8507068 A	14-07-1987
		CA 1249837 A	07-02-1989
		EP 0204730 A	17-12-1986
		WO 8603189 A	05-06-1986
		JP 6055684 B	27-07-1994
BE 892958 A	16-08-1982	AU 560590 B	09-04-1987
		AU 8336582 A	07-12-1982
		BR 8207962 A	04-10-1983
		CA 1229096 A	10-11-1987
		FI 831848 A	24-05-1983
		WO 8203854 A	11-11-1982
		GB 2116552 A,B	28-09-1983
		JP 4057655 B	14-09-1992
		JP 58500993 T	23-06-1983
		NL 191438 B	01-03-1995
		NL 8220121 T	01-07-1983
		SE 452154 B	16-11-1987
		SE 8303027 A	30-05-1983
		ZA 8202718 A	30-03-1983
US 4652685 A	24-03-1987	EP 0222398 A	20-05-1987
		JP 62155231 A	10-07-1987